

**A COMPOUND MOLD AND STRUCTURED SURFACE
ARTICLES CONTAINING GEOMETRIC STRUCTURES
WITH COMPOUND FACES AND METHOD OF MAKING SAME**

Background

The present invention relates generally to structured surfaces fabricated using microreplication techniques. The invention has particular application to structured surfaces that comprise retroreflective cube corner elements.

The reader is directed to the glossary at the end of the specification for guidance on the meaning of certain terms used herein.

It is known to use microreplicated structured surfaces in a variety of end use applications such as retroreflective sheeting, mechanical fasteners, and abrasive products. Although the description that follows focuses on the field of retroreflection, it will be apparent that the disclosed methods and articles can equally well be applied to other fields that make use of microreplicated structured surfaces.

Cube corner retroreflective sheeting typically comprises a thin transparent layer having a substantially planar front surface and a rear structured surface comprising a plurality of geometric structures, some or all of which include three reflective faces configured as a cube corner element.

Cube corner retroreflective sheeting is commonly produced by first manufacturing a master mold that has a structured surface, such structured surface corresponding either to the desired cube corner element geometry in the finished sheeting or to a negative (inverted) copy thereof, depending upon whether the finished sheeting is to have cube corner pyramids or cube corner cavities (or both). The mold is then replicated using any suitable technique such as conventional nickel electroplating to produce tooling for forming cube corner retroreflective sheeting by processes such as embossing, extruding, or cast-and-curing. U.S. Pat. No. 5,156,863 (Pricone et al.) provides an illustrative overview of a process for forming tooling used in the manufacture of cube corner retroreflective sheeting. Known methods for

manufacturing the master mold include pin-bundling techniques, laminate techniques, and direct machining techniques. Each of these techniques has its own benefits and limitations.

5 In pin bundling techniques, a plurality of pins, each having a geometric shape such as a cube corner element on one end, are assembled together to form a master mold. U.S. Patent Nos. 1,591,572 (Stimson) and 3,926,402 (Heenan) provide illustrative examples. Pin bundling offers the ability to manufacture a wide variety of cube corner geometry in a single mold, because each pin is individually machined. However, such techniques are impractical for making small cube corner elements (e.g. 10 those having a cube height less than about 1 millimeter) because of the large number of pins and the diminishing size thereof required to be precisely machined and then arranged in a bundle to form the mold.

In laminate techniques, a plurality of plate-like structures known as laminae, each lamina having geometric shapes formed on one end, are assembled to form a 15 master mold. Laminate techniques are generally less labor intensive than pin bundling techniques, because the number of parts to be separately machined is considerably smaller, for a given size mold and cube corner element. However, design flexibility suffers relative to that achievable by pin bundling. Illustrative examples of laminate techniques can be found in U.S. Patent No. 4,095,773 (Lindner); International 20 Publication No. WO 97/04939 (Mimura et al.); and U.S. Application Serial No. 08/886,074, "Cube Corner Sheeting Mold and Method of Making the Same", filed July 2, 1997.

In direct machining techniques, series of grooved side surfaces are formed in the plane of a planar substrate to form a master mold. In one well known embodiment, 25 three sets of parallel grooves intersect each other at 60 degree included angles to form an array of cube corner elements, each having an equilateral base triangle (see U.S. Patent No. 3,712,706 (Stamm)). In another embodiment, two sets of grooves intersect each other at an angle greater than 60 degrees and a third set of grooves intersects each of the other two sets at an angle less than 60 degrees to form an array of canted cube

corner element matched pairs (see U.S. Patent No. 4,588,258 (Hoopman)). Direct machining techniques offer the ability to accurately machine very small cube corner elements in a manner more difficult to achieve using pin bundling or laminate techniques because of the latter techniques' reliance on constituent parts that can move or shift relative to each other, and that may separate from each other, whether during construction of the mold or at other times. Further, direct machining techniques produce large area structured surfaces that generally have higher uniformity and fidelity than those made by pin bundling or laminate techniques, since, in direct machining, a large number of individual faces are typically formed in a continuous motion of the cutting tool, and such individual faces maintain their alignment throughout the mold fabrication procedure.

However, a significant drawback to direct machining techniques has been reduced design flexibility in the types of cube corner geometry that can be produced. By way of example, the maximum theoretical total light return of the cube corner elements depicted in the Stamm patent referenced above is approximately 67%. Since the issuance of that patent, structures and techniques have been disclosed which greatly expand the variety of cube corner designs available to the designer using direct machining. See, for example, U.S. Patent Nos. 4,775,219 (Appledorn et al.); 4,895,428 (Nelson et al.); 5,600,484 (Benson et al.); 5,696,627 (Benson et al.); and 5,734,501 (Smith). Some of the cube corner designs disclosed in these later references can exhibit effective aperture values well above 67% at certain observation and entrance geometry.

Nevertheless, an entire class of cube corner elements, referred to herein as "preferred geometry" or "PG" cube corner elements, have up until now remained out of reach of known direct machining techniques. A substrate incorporating one type of PG cube corner element is shown in the top plan view of Fig. 1. The cube corner elements shown there each have three square faces, and a hexagonal outline in plan view. One of the PG cube corner elements is highlighted in bold outline for ease of identification. The highlighted cube corner element can be seen to be a PG cube

corner element because it has a non-dihedral edge (any one of the six edges that have been highlighted in bold) that is inclined relative to the plane of the structured surface, and such edge is parallel to adjacent nondihedral edges of neighboring cube corner elements (each such edge highlighted in bold is not only parallel to but is contiguous with nondihedral edges of its six neighboring cube corner elements).

Disclosed herein are methods for making geometric structures, such as PG cube corner elements, that make use of direct machining techniques. Also disclosed are molds to manufacture articles according to such methods, such articles characterized by having at least one specially configured compound face.

Brief Summary

Structured surface articles such as molds or sheeting are formed on a compound substrate comprising a machined substrate and a replicated substrate. In one embodiment, the structured surface is a cube corner element on a compound substrate. In another embodiment, the structured surface comprises a geometric structure that has a plurality of faces, where one face is located on the machined substrate and another face is located on the replicated substrate. The geometric structure can optionally be a cube corner element or a PG cube corner element.

In yet another embodiment, at least some of the faces comprise a compound face with a portion formed on the machined substrate and a portion formed on the substantially replicated substrate. A transition line may separate the portion of a compound face located on the machined substrate from the portion located on the replicated substrate. The portion of the compound face on the machined substrate and the portion on the replicated substrate typically have angular orientations that differs by less than 10 degrees of arc.

Another embodiment is directed to a geometric structure having a plurality of faces disposed on a compound substrate. The compound substrate comprises a machined substrate having a structured surface and a substantially replicated substrate bonded along only a portion of an interface with the machined substrate.

In another embodiment, the compound substrate comprises a substantially replicated substrate having a structured surface and a discontinuous machined substrate covering only a portion of the structured surface. The compound substrate also comprises at least one geometric structure having at least one face disposed on the structured surface and at least another face disposed on the machined substrate.

Another embodiment is directed to a compound substrate comprising a substantially replicated substrate and a machined substrate. The replicated substrate has a structured surface and the machined substrate disposed in discrete pieces on the structured surface.

Another embodiment is directed to a compound mold having a structured surface comprising cavities formed in a replicated substrate and a plurality of pyramids bordering the cavities that are machined at least in part in a machined substrate of the compound substrate.

Cube corner elements, and structured surfaces incorporating an array of such elements, are disclosed wherein at least one face of the cube corner element terminates at a nondihedral edge of such element, the face comprising two constituent faces disposed on opposed sides of a transition line that is nonparallel to the nondihedral edge. The cube corner element can comprise a PG cube corner element where some or all of such elements comprise two constituent faces disposed on opposed sides of a transition line that is nonparallel to the respective nondihedral edge and the transition line comprises an interface between two adjacent layers of a compound substrate. In an array of neighboring cube corner elements, each cube corner element in the array can have at least one face configured as described above. Further, the cube corner elements can be made very small (well under 1 mm cube height) due to the direct machining techniques employed.

Also disclosed is a method of making a structured surface article comprising a geometric structure having a plurality of faces. The method comprises the steps of forming an array of geometric structures in a first surface of a machined substrate; passivating selected locations of the first surface of the machined substrate; forming a

replicated substrate of the machined substrate to form a compound substrate; forming an array of second geometric structures on a second surface opposite the first surface on the machined substrate; and removing selected portions from the second surface of the machined substrate to form an array of neighboring cube corner elements. The
5 cube corner elements can be PG cube corner elements.

In another embodiment, the method of making a structured surface article comprises the steps of forming an array of geometric structures in a first surface of a machined substrate; passivating selected locations of the first surface of the machined substrate; forming a replicated substrate of the machined substrate to form a
10 compound substrate; forming an array of second geometric structures on a second surface opposite the first surface on the machined substrate; and removing selected portions from the second surface of the machined substrate to form a geometric structure having a plurality of faces, wherein at least one of the faces is located on the machined substrate and at least one of the faces is located on the replicated substrate.

In another embodiment, the method of making a geometric structure in an article comprises providing a compound substrate having a structured surface formed along an internal interface between two substrates; and forming grooved side surfaces in an exposed surface of the compound substrate to form a geometric structure, the geometric structure comprising a portion of the internal interface and a portion of the
15 grooved side surfaces.
20

Brief Description of the Drawings

Fig. 1 is a plan view of a structured surface comprising one type of PG cube corner element array, known from the PRIOR ART.

25 Fig. 2 is a perspective view of an assembly including a machined substrate.

Fig. 3 is a sectional view of the substrate of Fig. 2.

Fig. 4 is a perspective view of the substrate of Fig. 2 after a first machining operation.

Fig. 5 is a close-up perspective view of a portion of the machined substrate illustrated in Fig. 4.

Fig. 6 is a sectional view of an assembly including a compound substrate.

Fig. 6a is an enlarged section of the compound substrate of Fig. 6.

5 Fig. 7 is a perspective view of the assembly of Fig. 6 with one of the machining bases removed.

Fig. 8 is a perspective view of the assembly of Fig. 7 with a portion of a blank surrounding the machined substrate removed.

10 Fig. 9 is cross-sectional view of the machining of the compound substrate of Fig. 7.

Fig. 10 is a perspective view of the compound substrate of Fig. 8 after the second machining operation.

Fig. 11 is a top view of Fig. 10.

15 Figs. 12-14 are top plan views of structured surfaces having canted PG cube corner elements, such surfaces being capable of fabrication using the methods discussed in connection with Figs. 2-11.

Fig. 15 is a top plan view of an alternate machined substrate in accordance with the present invention.

Fig. 16 is a sectional view of the substrate of Fig. 15.

20 Fig. 17 is a sectional view of the substrate of Fig. 15 with a passivated surface.

Fig. 18 is a top plan view of the substrate of Fig. 17 with portions of the passivated surface removed.

Fig. 19 is a sectional view of the substrate of Fig. 18.

Fig. 20 is a sectional view of an assembly including a compound substrate.

25 Fig. 21 is a top plan view of the machining of the compound substrate of Fig. 20.

Fig. 22 is a sectional view of the substrate of Fig. 21.

Fig. 23 is a top plan view of the compound substrate of Fig. 21 after the second machining operation.

In the drawings, the same reference symbol is used for convenience to indicate elements that are the same or that perform the same or a similar function.

Detailed Description of the Illustrative Embodiments

5 Figs. 2 and 3 illustrate an assembly 20 useful for making a structured surface (see Figs. 9-10) in accordance with the present invention. The assembly 20 includes a blank 22 bonded to a first machining base 24 by a first bonding layer 26. In the illustrated embodiment, the blank 22 is a continuous structure that includes a deck 27 and a series of reference pads 30a, 30b, 30c, 30d, 30e, 30f (collectively referred to as
10 30) that extend above surface 32. In one embodiment, the deck 27 has a height 34 generally equal to a height 36 of the reference pads 30. The number of reference pads 30 can vary depending upon the application. In an alternate embodiment, the deck 27 and the reference pads 30 can be discrete elements bonded to the first machining base 24, rather than the continuous blank 22 shown in Fig. 2.

15 Blank 22 is composed of a material that can be scribed, cut, or otherwise machined without significant post-machining deformation and without substantial burring. This is to ensure that the machined faces, or replications thereof in other substrates, can function as effective optical reflectors. The blank 22 may be constructed from various materials, such as copper, nickel, aluminum, acrylic, or other
20 polymeric materials. Further discussion on suitable substrate materials is given below. In one embodiment, the blank 22 is a thin metal sheet material approximately 0.030 inches thick.

The blank 22 is bonded to a first machining base 24 using a suitable bonding layer 26, such as epoxy, wax, thermoform or thermoset adhesives, and the like. In the
25 illustrated embodiment, the first machining base 24 is a metal plate approximately 2.54 centimeters (1.0 inch) thick. The first machining base 24 supports the relatively thin blank 22 and provides reference surfaces 38 for subsequent machining operations. Although the circular shape of the assembly 20 is convenient for subsequent electroplating operations, the circular shape is not required.

Fig. 4 depicts the machining operation to form a machined substrate 28 in the deck portion 27 of the blank 22. Cutting tools 40a, 40b, 40c (collectively referred to as 40) move along the deck 27 (see Fig. 2) to form a structured surface 50 of machined substrate 28, whether by motion of the cutting tools or the substrate or both, to form groove side surfaces (see Fig. 5). The cutting tool 40a forms reference grooves 44c, 44f in respective reference pads 30c, 30f, cutting tool 40b forms reference grooves 44a, 44d in respective reference pads 30a, 30d, and cutting tool 40c forms reference grooves 44b, 44e in respective reference pads 30b, 30e. A circular reference groove 46a, 46b, 46c, 46d, 46e, 46f concentric with the center of the machined substrate 28 is optionally formed in each of the respective reference pads 30. Reference marks 43 may optionally be formed on the edge of the modified blank 22' to assist in locating the compound substrate 82 to perform the cutting operations illustrated in Fig. 7.

Each tool 40 is depicted as a so-called "half-angle" tool, which produces grooved side surfaces as it progresses through the material rather than a pair of opposed groove side surfaces, although this is not necessary. In the illustrated embodiment, one of the grooved side surfaces is substantially vertical (see Fig. 5). Consistent with direct machining procedures, cutting tools 40 move along axes 42a, 42b, 42c that are substantially parallel to the x-y reference plane defined by the reference surface 38, thus ensuring that the respective groove side surfaces also extend along axes that are substantially parallel to the reference plane. In the illustrated embodiment, each of the axes 42a, 42b, 42c intersect two of the reference pads 30. Preferably, the axes 42a, 42b, 42c are carefully positioned and the tool orientation carefully selected so that the groove side surfaces have a generally uniform depth.

It should be noted that although three cutting tools are shown in Fig. 4, a single cutting tool could be used. The cutting tool can be made of diamond or other suitably hard material. The machined faces can be formed by any one of a number of known material removal techniques, for example: milling, where a rotating cutter, spinning about its own axis, is tilted and drawn along the surface of the substrate; fly-cutting, where a cutter such as a diamond is mounted on the periphery of a rapidly rotating

wheel or similar structure which is then drawn along the surface of the substrate; ruling, where a nonrotating cutter such as a diamond is drawn along the surface of the substrate; and grinding, where a rotating wheel with a cutting tip or edge is drawn along the surface of the substrate. Of these, preferred methods are those of fly-cutting and ruling. It is not critical during the machining operation whether the cutting tool, the substrate, or both are translated relative to the surroundings. Full-angle cutting tools are preferred when possible over half-angle tools because the former are less prone to breakage and allow higher machining rates. Finally, cutting tools having a curved portion or portions can be used in the disclosed embodiments to provide non-flat (curved) surfaces or faces in order to achieve desired optical or mechanical effects.

Fig. 5 shows an enlarged section of the structured surface 50 machined in the machined substrate 28 illustrated in Fig. 4. Structured surface 50 includes faces 54 arranged in groups of three that form cube corner pyramids 56. Interspersed between cube corner pyramids 56 on structured surface 50 are protrusions 58. The protrusions 58 as shown each have three mutually perpendicular side surfaces 60, three generally vertical surfaces 61, and a top surface 62. Depending on the procedure used to make the structured surface 50, the generally vertical surfaces 61 of the protrusions 58 can be inclined to a greater or lesser extent away from the vertical. In the illustrated embodiment, the cube corner pyramids 56 cover about 50% of the machined substrate and the protrusions 58 cover the other 50% of the substrate.

The structured surface 50 is then cleaned and passivated. The passivation step comprises applying a release layer or modifying the surface 50 to permit separation of a subsequent replicated substrate 70 (see Fig. 6). In an embodiment where the blank 22 is constructed from metal, such as copper, the structured surface 50 can be passivated with potassium dichromate or other passive solutions. In an embodiment where the blank 22 is constructed from acrylic or another polymeric material, vapor coated or chemically deposited silver can be used to create the release layer. The passivation step can be modified depending upon the material used for the machined substrate 28 and the replicated substrate 70.

In order to permit selective adhesion of the replicated substrate 70 to the structured surface 50, the top surfaces 62 of the protrusions 58 are treated. In one embodiment, the top surfaces 62 are abraded. Abrasion of the top surfaces 62 can be accomplished using a planarization process, fly cutting, or a variety of other processes.

5 Figs. 6 and 6a illustrate an assembly 81 that results after forming a replicated substrate 70 over the machined substrate 28 and the reference pads 30. Electroplating, casting a filler material, and a variety of other techniques can form the replicated substrate 70. The thickness of the replicated substrate 70 is a matter of design choice. In the illustrated embodiment, the replicated substrate 70 has a
10 thickness of about 2 times the height of the desired cube corner elements.

As best illustrated in Fig. 6a, due to the previous passivation and abrasion steps, the replicated substrate 70 adheres to the structured surface 50 along the top surface 62 of the protrusions 58, but not along the passivated surfaces of the pyramids 56 and the side surfaces 60, 61 of the protrusions 58. Portions of the replicated
15 substrate 70 protrude into the machined substrate 28 to form a compound substrate 82 (see also Fig. 9). A second machining base 74 is bonded to rear surface 76 of the replicated substrate 70 using a suitable bonding layer 78. Like the first machining base 24, the second machining base 74 includes reference surfaces 80 to aid in subsequent machining steps. The first machining base 24 and bonding layer 26 are no longer
20 needed for the process and are removed from the assembly 20.

Fig. 7 is a perspective view of an assembly 81 comprising the modified blank 22' (machined substrate 28 and reference pads 30) selectively bonded to the replicated substrate 70. The replicated substrate 70 is bonded to the second machining base 74 by the bonding layer 78. In the illustrated embodiment, rear surface 71 of the modified
25 blank 22' is substantially flat. The compound substrate 82 and reference pads 30 embedded in the assembly 81 are shown in phantom for purposes of illustration only.

A series of four cuts are made around the perimeter P1, P2, P3, P4 of compound substrate 82, permitting the portions of the modified blank 22' surrounding the machined substrate 28 to be removed from the assembly 81. Reference marks 43

2
Fig 6a.

may optionally be used to locate the compound substrate 82. The passivation layer facilitates removal of this waste material. In an embodiment where the blank 22 and replicated substrate 70 are constructed from metal, the portion of the blank 22 surrounding the machined substrate 28 is a thin layer that can be peeled from the replicated substrate 70.

Fig. 8 is a perspective view of a modified assembly 83 with the portions of the blank 22 surrounding the compound substrate 82 removed. Surface 85 is of the replicated substrate 70. Surface 90, which extends above the surface 85, is the back surface of the machined substrate 28. Reference pad replicas 84a, 84b, 84c, 84d, 84e, 84f (collectively referred to as 84) of the reference pads 30 define cavities in the surface 85. The reference pad replicas 84a, 84d have respective parallel ridges 86a, 86d, replicas 84b, 84e have respective parallel ridges 86b, 86e, and replicas 84c, 84f have respective parallel ridges 86c, 86f (collectively referred to as 86). Each of the reference pad replicas 84 has a ridge 88a, 88b, 88c, 88c, 88d, 88e, 88f (collectively referred to as 88), respectively, defining a circle concentric with the center of the compound substrate 82. In the illustrated embodiment, the tops of the ridges 86, 88 are generally coplanar with the surface 85.

Fig. 9 is a schematic illustration of the machining step performed on the back surface 90 of the machined substrate 28. In the illustrated embodiment, the compound substrate 82 comprises the machined substrate 28 and the un-separated replicated substrate 70. The interface 92 between the structured surface 50 and the replicated substrate 70 is indicated by dashed line. Bonding at the interface 92, however, is limited to the abraded top surfaces 62 of the protrusions 58. The passivation layer prevents or minimizes adhesion along the remainder of the interface 92, such as along the pyramids 56 or the side surfaces 60, 61 of the protrusions 58.

The machining step illustrated in Fig. 4 is then performed on the back surface 90 of the machined substrate 28 using the ridges 86, 88 as reference points to guide tool 101. The tool 101 may or may not be a half-angle tool. In an embodiment where the machined substrate 28 and/or the replicated substrate 70 are formed from a

transparent or semi-transparent material, or where the interface between the machined substrate 28 and replicated substrate 70 can be viewed along the perimeter P1, P2, P3, P4 of compound substrate 82, the reference pad replicas 84 may be unnecessary. That is, alignment of the tools 42a, 42b, 42c can be accomplished without resort to the reference pad replicas 84. Where the machined substrate 28 is formed from an opaque material such as metal, the reference pad replicas 84 (and particularly the ridges 86) provide precise reference points so that the machining step illustrated in Fig. 9 can be performed.

After cuts are made along all three axes 42a, 42b, 42c, waste portions 94 of the machined substrate 28 fall away or are removed, leaving a cube corner cavity 118 in the replicated substrate 70. In some embodiments, the tool 101 may cut into the replicated substrate 70 such that the replicated substrate may include a replicated or formed portion and a machined portion. The distal ends or top surfaces 62 of the discrete pieces or protrusions 58 from the machined substrate 28 are bonded to the replicated substrate 70. Bottom or proximal portions of the protrusions 58 are machined to form cube corner pyramids 120a. The protrusions 58 on the machined substrate 28 remain embedded in the replicated substrate 70. Once all of the waste portions 94 of the machined substrate 28 are removed from the replicated substrate 70, the cube corner pyramids 120a and cube corner cavities 118 form a geometric structured surface 100 with an array of PG cube corner elements (see Fig. 10).

Fig. 10 is a view of a geometric structured surface 100 on compound substrate 82 after all groove side surfaces have been formed. Each of the cube corner cavities 118 has three replicated faces 116a, 116b, 116c and each of the cube corner pyramids 120a has three machined faces 126a, 126b, 126c, configured approximately mutually perpendicular to each other. In the case where the three faces of a cube corner pyramid 120a are substantially aligned with adjacent faces 116 of cavities 118, and where such cavities 118 have a common orientation, the three faces of cube corner pyramid 120a (when considered separately) form a "truncated" cube corner pyramid. Such a

pyramid is characterized by having exactly three nondihedral edges that form a “base triangle” in the plane of the structured surface.

Each of the three faces 126a-c of the cube corner pyramids 120a are machined to be substantially aligned with the nearest face 116 of an adjacent cube corner cavity 118. Consequently, each new cube corner cavity 132 comprising one replicated cube corner cavity 118 and one machined face 126 from each of its neighboring geometric structures 120a. Reference numeral 132a shows in bold outline one such cube corner cavity 132. A given face of one of the cube corner cavities 132 comprises one face of a cube corner cavity 118 formed in the replicated substrate 70 and one of the faces 126a, 126b, or 126c machined in the machined substrate 28. As will be discussed *infra*, faces 116 of the cube corner cavity 118 are machined in the replicated substrate 70. Therefore, each cube corner cavity 132 comprises a compound face made up of a portion substantially formed or replicated in the replicated substrate 70 and a portion machined in the machined substrate 28 separated by a transition line 130. The transition lines 130 lie along the boundary or interface between the machined substrate 28 and the replicated substrate 70.

One can also identify new cube corner pyramids 134 formed on the structured surface shown in Fig. 10. Each cube corner pyramid 134 comprises one geometric structure 120a, which is a cube corner pyramid, and one face each of its neighboring cube corner cavities 118. Each face of one of the pyramids 134 is a compound face comprising a face 116 of one of the cavities 118 in the replicated substrate 70 and a machined face from structure 120a formed from the machined substrate 28. Reference numeral 134a shows in bold outline of one such cube corner pyramid 134. Note that the reference points 122 locate the uppermost extremities or peaks of the pyramids 134. Both cube corner pyramids 134 and cube corner cavities 132 are PG cube corner elements, since both have a face terminating at a nondihedral edge of the cube corner element, such nondihedral edge being nonparallel to reference plane x-y.

Fig. 11 shows a top view of the structured surface of Fig. 10. Transition lines 130 are drawn narrower than other lines to aid in identifying the PG cube corner

elements, i.e. cube corner cavities 132 and cube corner pyramids 134. The compound faces of such PG cube corner elements extend across opposite sides of the transition lines 130 separating discrete pieces of the machined substrate 28 from the replicated substrate 70, to which they are bonded. In the illustrated embodiment, all transition

5 lines 130 lie in a common plane referred to as a transition plane, which in the case of this embodiment is coplanar with the x-y plane. The faces of the structured surface machined in the machined substrate 28 are disposed on one side of the transition plane and the faces machined in the replicated substrate 70 are disposed on the other side.

The machined cube corner article of Figs. 10-11 can itself function as a

10 retroreflective article, both with respect to light incident from above (by virtue of cube-corner cavities 132) and, where the substrate is at least partially transparent, with respect to light incident from below (by virtue of cube corner pyramids 134). In either case, depending upon the composition of the substrate, a specularly reflective thin coating such as aluminum, silver, or gold can be applied to the structured surface to

15 enhance the reflectivity of the compound faces. In the case where light is incident from below, reflective coatings can be avoided in favor of an air interface that provides total internal reflection.

More commonly, however, the compound substrate of Figs. 10-11 is used as a mold from which end-use retroreflective articles are made, whether directly or through

20 multiple generations of molds, using conventional replication techniques. Each mold or other article made from the compound substrate will typically contain cube corner elements having at least one face terminating at a nondihedral edge of the cube corner element, the at least one face comprising two constituent faces disposed on opposed sides of a transition line, the transition line being nonparallel to such nondihedral edge.

25 As seen from Figs. 10-11, transition lines 130 lie in the transition plane coincident with the x-y plane, whereas nondihedral edges shown in bold for both PG cube corner cavity 132 and PG cube corner pyramid 134 are inclined relative to the x-y plane. It is also possible to fabricate surfaces where the transition lines do not all lie in the same plane, by forming groove side surfaces at different depths in the substrate.

Transition lines can in general take on a great variety of forms, depending upon details of the cutting tool used and on the degree to which the motion of the cutting tool is precisely aligned with other faces in the process of forming groove side surfaces. Although in many applications transition lines are an artifact to be
5 minimized, in other applications they can be used to advantage to achieve a desired optical result such as a partially transparent article. A detailed discussion of various transition line configurations is set forth in commonly assigned U.S. Patent Application Serial No. _____ (Attorney Docket No. 54222USA_A) filed on the same date herewith, entitled Structured Surface Articles Containing Geometric Structures
10 with Compound Faces and Methods for Making Same, which is incorporated by reference.

A wide variety of structured surfaces can be fabricated using the present compound substrate 82 and the machining technique described above. The PG cube corner elements of Fig. 11 each have a symmetry axis that is perpendicular to the x-y
15 reference plane of the structured surface. Cube corner elements typically exhibit the highest optical efficiency in response to light incident on the element roughly along the symmetry axis. The amount of light retroreflected by a cube corner element generally drops as the incidence angle deviates from the symmetry axis. Fig. 12 shows a top plan view of a structured surface 136 similar to that of Fig. 11, extending along the x-y
20 plane, except that the PG cube corner elements of Fig. 12 are all canted such that their symmetry axes are tilted with respect to the normal of the structured surface. The symmetry axis for each PG cube corner cavity 146 in Fig. 12 lies in a plane parallel to the y-z plane, having a vertical component in the +z direction (out of the page) and a transverse component in the +y direction. Symmetry axes for the PG cube corner
25 pyramids 148 of Fig. 12 point in the opposite direction, with components in the -z and -y directions. In fabricating surface 136, a compound substrate is used wherein the protrusions of generally triangular cross-section are isosceles in shape, rather than equilateral as in Fig. 1.

Four distinct types of cube corner elements are present on the structured surface 136: truncated cube corner cavities formed in replicated substrate 70 and a triangular outline in plan view; truncated cube corner pyramids having faces machined in discrete pieces of the machined substrate 28 and triangular outline; PG cube corner cavities having compound faces and a hexagonal outline; and PG cube corner pyramids, also having compound faces and a hexagonal outline. A representative cube corner cavity formed in the replicated substrate 70 is identified in Fig. 12 by bold outline 140, and a representative cube corner pyramid machined in the machined substrate 28 is identified by bold outline 142. Transition lines 144 separate machined from formed or replicated faces, and all such lines 144 lie in a transition plane parallel to the x-y plane. In other embodiments, the transition lines may lie parallel to a transition plane but not be coplanar. Selected faces of cavities 140 and pyramids 142 form canted PG cube corner elements, in particular canted PG cube corner cavities 146 and canted PG cube corner pyramids 148. Reference points 122, as before, identify localized tips or peaks disposed above the x-y plane.

Fig. 13 shows a structured surface 136a similar to that of Fig. 12, and like features bear the same reference numeral as in Fig. 12 with the added suffix “a”. PG cube corner elements of Fig. 13 are canted with respect to the normal of structured surface 136a, but in a different direction compared to that of the PG cube corner elements of Fig. 12. The symmetry axis for each PG cube corner cavity 146a is disposed in a plane parallel to the y-z plane, and has a vertical component in the +z direction and a transverse component in the -y direction.

Fig. 14 shows a structured surface similar to that of Figs. 12 and 13, and like features bear the same reference numeral as in Fig. 12 with the added suffix “b”. PG cube corner elements in Fig. 14 are also canted, but, unlike the PG cube corner elements of Figs. 12 and 13, the degree of cant is such that the outline in plan view of each PG cube corner element has no mirror-image plane of symmetry. The cube corner cavities of Fig. 14 each have a symmetry axis that has components in the +z, +y, and -x direction. It will be noted that the triangles formed by transition lines 144

(Fig. 12) are isosceles triangles each having only one included angle less than 60 degrees; triangles formed by lines 144a (Fig. 13) are isosceles triangles each having only one included angle greater than 60 degrees; and triangles formed by lines 144b (Fig. 14) are scalene triangles. Representative values in degrees for the included
5 angles of triangles defined by transition lines 144a are, respectively: (70, 70, 40); (80, 50, 50); and (70, 60, 50).

The embodiments discussed above have associated therewith an asymmetrical entrance angularity (i.e., when rotated about an axis within the plane of the sheeting). Embodiments with symmetrical entrance angularity are also possible, such as the
10 matched-pair cube corner structure discussed in connection with Figs. 15-23.

Figs. 15 and 16 depict an alternate machined substrate 200 in accordance with the present invention. The machined substrate 200 is bonded to a first machining base 202 by a first bonding layer 204. Two sets of grooves 206, 208 parallel to axis 207a 207b, respectively, are formed using tools 201a, 201b to define a machined surface
15 212. In the illustrated embodiment, the machined surface 212 includes faces 213 arranged in groups of four that form four-sided pyramids 210 having an apex or reference point 215. The four-sided pyramids 210 are arranged in rows 217, 222, 223. Other geometric structures 211 are also formed by the grooves 206, 208.

As illustrated in sectional view Fig. 17, the machined surface 212 is then
20 cleaned and passivated. The passivation step comprises applying a release layer or making a surface modification 216 (referred to collectively as "passivated surface") on the machined surface 212 to permit separation of a subsequent replicated substrate 214 (see Fig. 20). In one embodiment, the passivated surface is formed on only a portion of the machined surface 212.

25 As illustrated in Figs. 18 and 19, additional grooves 220a, 220b, 220c (referred to collectively as 220) are formed in the machined surface 212 parallel to axis 207c using tool 201c in order to remove portions of some of the geometric structures 211. The grooves 220 also remove some of the surface modification 216 to permit selective adhesion of the replicated substrate 214 (see Fig. 20) to the machined surface 212. As

best illustrated in Figure 19, the passivated surface 216 is not present along flat regions 228 or along side walls 230, while the passivated surface 216 on faces 213 is substantially intact.

Fig. 20 illustrates an assembly 232 that results after forming a replicated substrate 214 over the machined substrate 200'. Electro-plating, casting a filler material, and a variety of other techniques can form the replicated substrate 214. Due to the previous passivation step, the replicated substrate 214 adheres to the flat regions 228 and side walls 230, but not along the passivated surfaces 216. Portions 234 of the replicated substrate 214 protrude into, and bond with, the machined substrate 200' along surfaces 228, 230 to form a compound substrate 236. A second machining base 250 is bonded to rear surface 252 of the replicated substrate 214 using a suitable bonding layer 254. Like the first machining base 202, the second machining base 250 includes reference surfaces (see Fig. 3) to aid in subsequent machining steps. The first machining base 202 and bonding layer 204 are no longer needed for the process and are removed from the assembly 232. The second machining base 250 supports the compound substrate 236 during machining of the back surface 260, discussed below.

Figs. 21 and 22 illustrate the machining step performed on the back surface 260 of the compound substrate 236. Grooves 268a, 268b, 268c are formed along axes 270a, 270b, 270c using tools 272a, 272b, 272c. The grooves 268a, 268b, 268c may extend into the replicated substrate 214. Waste portions 274 are not bonded to the replicated substrate 214 because of the passivation layer 216. Consequently, after the grooves 268 are made along all three axes 270, waste portions 274 fall away or are removed, leaving four-sided cavities 276 in the replicated substrate 214.

Discrete pieces or portions 278, 280 of the compound substrate 236, however, are bonded to the replicated substrate 214 along surfaces 230. Bottom or proximal portions of the portions 278, 280 are machined to form three-sided pyramids 282. The portions 278, 280 of the machined substrate 200' remain embedded in the replicated substrate 214 portion of the compound substrate 236. Once all of the waste portions 274 of the compound substrate 236 are removed from the replicated substrate 214,

thus exposing all of the four-sided cavities 276, the three-sided pyramids 282 and four-sided cavities 276 form a geometric structured surface 290 comprising an array of PG cube corner elements (see Fig. 23).

In an embodiment where the machined substrate 200' and/or the replicated
5 substrate 214 are formed from a transparent or semi-transparent material, or where the interface between the machined substrate 200' and replicated substrate 214 can be viewed along the perimeter of compound substrate 236, reference pads such as illustrated in connection with Figs. 2-8 may be unnecessary. That is, alignment of the tools can be accomplished without resort to the reference pad. Where the machined
10 substrate 200' is formed from an opaque material such as metal, reference pads such as illustrated in Fig. 2 provide precise reference points so that the machining step illustrated in FIG. 21 can be performed.

Fig. 23 illustrates the geometric structured surface 290 after all groove side surfaces have been formed. This geometry results in two different types of PG cube
15 corner elements on the structured surface. Cube corner pyramid 296 has face g and compound faces h, h'; i, i' separated by transition lines a and b, respectively. Cube corner pyramid 298 has face j and compound faces k, k'; l, l' separated by transition lines c and d, respectively. Faces g and j are polygons with more than three sides. Consequently, in the top view of Fig. 23, the cube corner pyramids 296, 298 each have
20 a rectangular shape as shown by the respective dashed outlines, rather than a hexagonal outline as depicted in FIGS. 10-14. In an embodiment where the grooves 272c are all of the same depth, the cube corner elements 296 and 298 are opposing or matched pair cube corner elements that provide symmetric entrance angularity. Depending upon the aspect ratio, the plan view rectangular outlines of the cube corner
25 elements can also include a square outline.

Cube corner elements of Fig. 23 can be (forward or backward) canted or uncanted as desired. Producing cube corner elements that are canted to a greater or lesser degree is accomplished by tailoring the shape of the diamond-shaped protrusions and then the orientation of the groove side surfaces (g, h, i, j, k, l) to be in

conformance with the desired degree of canting. If canting is used, then such matched pairs can, in keeping with principles discussed in U.S. Patent Nos. 4,588,258 (Hoopman), 5,812,315 (Smith et al.), and 5,822,121 (Smith et al.), give rise to widened retroreflective angularity so that an article having the structured surface will be visible over a widened range of entrance angles.

During the present machining process, the cutting tool removes a relatively large amount of material because the angle between the steeply inclined side wall and the subsequent machined face is often in excess of 10 degrees, typically ranging from about 10 to about 45 degrees. Some of the groove side surfaces can then be formed in such a modified machined substrate by leaving more material on the cavities or protrusions during either or both machining steps, thereby reducing tool forces which could detrimentally cause distortions. Another benefit is less wear on the cutting tool. A modified machined substrate can also be used as a master from which future generations of positive/negative molds can be made. Various geometric configurations for modified machined substrate are disclosed in commonly assigned U.S. Patent Application Serial No. _____ (Attorney Docket No. 54222USA1A) filed on the same date herewith, entitled Structured Surface Articles Containing Geometric Structures with Compound Faces and Methods for Making Same, which is incorporated by reference.

The cube corner elements disclosed herein can be individually tailored so as to distribute light retroreflected by the articles into a desired pattern or divergence profile, as taught by U.S. Pat. No. 4,775,219 (Appledorn et al.). For example, compound faces that make up the PG cube corner elements can be arranged in a repeating pattern of orientations that differ by small amounts, such as a few arc-minutes, from the orientation that would produce mutual orthogonality with the other faces of cube corner element. This can be accomplished by machining groove side surfaces (both those that ultimately become the faces in the finished mold below the transition plane as well as those that become faces in the finished mold above the transition plane) at angles that differ from those that would produce mutually orthogonal faces by an

amount known as a “groove half-angle error”. Typically the groove half-angle error introduced will be less than ± 20 arc minutes and often less than ± 5 arc minutes. A series of consecutive parallel groove side surfaces can have a repeating pattern of groove half-angle errors such as abbaabba... or abcdabcd..., where a, b, c, and d are
5 unique positive or negative values. In one embodiment, the pattern of groove half-angle errors used to form faces in the finished mold above the transition plane can be matched up with the groove half-angle errors used to form faces in the finished mold below the transition plane. In this case, the portions of each compound face on the machined substrate and the replicated substrate will be substantially angularly aligned
10 with each other. In another embodiment, the pattern used to form one set of faces can differ from the pattern used to form the other, as where the faces below the transition plane incorporate a given pattern of nonzero angle errors and faces above the transition plane incorporate substantially no angle errors or a different pattern of non-zero errors. In this latter case, the portions of each compound face on the machined substrate and
15 the replicated substrate will not be precisely angularly aligned with each other.

Advantageously, such substrates can serve as a master substrate from which future generations of positive/negative molds can be made, all having the same general shape of cube corner element in plan view but having slightly different face configurations. One such daughter mold can incorporate cube corner elements that
20 each have compound faces whose constituent faces are aligned, the compound faces all being mutually perpendicular to the remaining faces of the cube corner element. Another such daughter mold can incorporate cube corner elements that also have compound faces whose constituent faces are aligned, but the compound faces can differ from orthogonality with remaining faces of the cube corner element. Still
25 another such daughter mold can incorporate cube corner elements that have compound faces whose constituent faces are not aligned. All such daughter molds can be made from a single master mold with a minimal amount of material removed by machining.

The working surface of the mold substrates can have any suitable physical dimensions, with selection criteria including the desired size of the final mold surface

and the angular and translational precision of the machinery used to cut the groove surfaces. The working surface has a minimum transverse dimension that is greater than two cube corner elements, with each cube corner element having a transverse dimension and/or cube height preferably in the range of about 25 μm to about 1 mm, and more preferably in the range of about 25 μm to about 0.25 mm. The working surface is typically a square several inches on a side, with four inch (10 cm) sides being standard. Smaller dimensions can be used to more easily cut grooves in registration with formed surfaces over the whole structured surface. The substrate thickness can range from about 0.5 to about 2.5 mm. (The measurements herein are provided for illustrative purposes only and are not intended to be limiting.) A thin substrate can be mounted on a thicker base to provide rigidity. Multiple finished molds can be combined with each other e.g. by welding in known tiling arrangements to yield a large tiled mold that can then be used to produce tiled retroreflective products.

15 In the manufacture of retroreflective articles such as retroreflective sheeting, the structured surface of the machined substrate is used as a master mold that can be replicated using electroforming techniques or other conventional replicating technology. The structured surface can include substantially identical cube corner elements or can include cube corner elements of varying sizes, geometry, or orientations. The structured surface of the replica, sometimes referred to in the art as a 'stamper', contains a negative image of the cube corner elements. This replica can be used as a mold for forming a retroreflective article. More commonly, however, a large number of suitable replicas are assembled side-by-side to form a tiled mold large enough to be useful in forming tiled retroreflective sheeting. Retroreflective sheeting can then be manufactured as an integral material, e.g. by embossing a preformed sheet with an array of cube corner elements as described above or by casting a fluid material into a mold. See, JP 8-309851 and U.S. Patent No. 4,601,861 (Pricone).
Alternatively, the retroreflective sheeting can be manufactured as a layered product by casting the cube corner elements against a preformed film as taught in PCT application

No. WO 95/11464 (Benson, Jr. et al.) and U.S. Pat. No. 3,684,348 (Rowland) or by laminating a preformed film to preformed cube corner elements. By way of example, such sheeting can be made using a nickel mold formed by electrolytic deposition of nickel onto a master mold. The electroformed mold can be used as a stamper to
5 emboss the pattern of the mold onto a polycarbonate film approximately 500 μm thick having an index of refraction of about 1.59. The mold can be used in a press with the pressing performed at a temperature of approximately 175° to about 200° C.

The various mold substrates discussed above can generally be categorized into two groups: replicated substrates, which receive at least part of their structured surface
10 by replication from a prior substrate, and bulk substrates, which do not. Suitable materials for use with bulk mold substrates are well known to those of ordinary skill in the art, and generally include any material that can be machined cleanly without burr formation and that maintains dimensional accuracy after groove formation. A variety of materials such as machinable plastics or metals may be utilized. Acrylic is an
15 example of a plastic material; aluminum, brass, electroless nickel, and copper are examples of useable metals.

Suitable materials for use with replicated mold substrates that are not subsequently machined are well known to those of ordinary skill in the art, and include a variety of materials such as plastics or metals that maintain faithful fidelity to the
20 prior structured surface. Thermally embossed or cast plastics such as acrylic or polycarbonate can be used. Metals such as electrolytic nickel or nickel alloys are also suitable.

Suitable materials for use with replicated mold substrates whose structured surface is subsequently machined are also well known to those of ordinary skill in the
25 art. Such materials should have physical properties such as low shrinkage or expansion, low stress, and so on that both ensure faithful fidelity to the prior structured surface and that lend such materials to diamond machining. A plastic such as acrylic (PMMA) or polycarbonate can be replicated by thermal embossing and then

subsequently diamond machined. Suitable hard or soft metals include electrodeposited copper, electroless nickel, aluminum, or composites thereof.

With respect to retroreflective sheeting made directly or indirectly from such molds, useful sheeting materials are preferably materials that are dimensionally stable,
5 durable, weatherable and readily formable into the desired configuration. Examples of suitable materials include acrylics, which generally have an index of refraction of about 1.5, such as Plexiglas resin from Rohm and Haas; thermoset acrylates and epoxy acrylates, preferably radiation cured, polycarbonates, which have an index of refraction of about 1.6; polyethylene-based ionomers (marketed under the name 'SURLYN');
10 polyesters; and cellulose acetate butyrates. Generally any optically transmissive material that is formable, typically under heat and pressure, can be used. Other suitable materials for forming retroreflective sheeting are disclosed in U.S. Pat. No. 5,450,235 (Smith et al.). The sheeting can also include colorants, dyes, UV absorbers, or other additives as needed.

15 It is desirable in some circumstances to provide retroreflective sheeting with a backing layer. A backing layer is particularly useful for retroreflective sheeting that reflects light according to the principles of total internal reflection. A suitable backing layer can be made of any transparent or opaque material, including colored materials, that can be effectively engaged with the disclosed retroreflective sheeting. Suitable
20 backing materials include aluminum sheeting, galvanized steel, polymeric materials such as polymethyl methacrylates, polyesters, polyamids, polyvinyl fluorides, polycarbonates, polyvinyl chlorides, polyurethanes, and a wide variety of laminates made from these and other materials.

The backing layer or sheet can be sealed in a grid pattern or any other
25 configuration suitable to the reflecting elements. Sealing can be affected by use of a number of methods including ultrasonic welding, adhesives, or by heat sealing at discrete locations on the arrays of reflecting elements (see, e.g. U.S. Pat. No. 3,924,928). Sealing is desirable to inhibit the entry of contaminants such as soil and/or

moisture and to preserve air spaces adjacent the reflecting surfaces of the cube corner elements.

If added strength or toughness is required in the composite, backing sheets of polycarbonate, polybutyrate or fiber-reinforced plastic can be used. Depending upon the degree of flexibility of the resulting retroreflective material, the material can be rolled or cut into strips or other suitable designs. The retroreflective material can also be backed with an adhesive and a release sheet to render it useful for application to any substrate without the added step of applying an adhesive or using other fastening means.

10 Glossary of selected terms

An "array of neighboring cube corner elements" means a given cube corner element together with all adjacent cube corner elements bordering it.

"Compound face" means a face composed of at least two distinguishable faces (referred to as "constituent faces") that are proximate each other. The constituent faces are substantially aligned with one another, but they can be offset translationally and/or rotationally with respect to each other by relatively small amounts (less than about 10 degrees of arc, and preferably less than about 1 degree of arc) to achieve desired optical effects as described herein.

"Compound substrate" means a substrate formed from a machined substrate having a structured surface and a replicated substrate (collectively referred to as "layers") bonded along at least a portion of the interface with the machined substrate. One or more of the layers of the compound substrate may be discontinuous.

"Cube corner cavity" means a cavity bounded at least in part by three faces arranged as a cube corner element.

25 "Cube corner element" means a set of three faces that cooperate to retroreflect light or to otherwise direct light to a desired location. Some or all of the three faces can be compound faces. "Cube corner element" also includes a set of three faces that itself does not retroreflect light or otherwise direct light to a desired location, but that if copied (in either a positive or negative sense) in a suitable substrate forms

a set of three faces that does retroreflect light or otherwise direct light to a desired location.

“Cube corner pyramid” means a mass of material having at least three side faces arranged as a cube corner element.

- 5 “Cube height” means, with respect to a cube corner element formed on or formable on a substrate, the maximum separation along an axis perpendicular to the substrate between portions of the cube corner element.

- “Dihedral edge” of a cube corner element is an edge of one of the three faces of the cube corner element that adjoins one of the two other faces of the same cube corner element. Note that any particular edge on a structured surface may or may not be a dihedral edge, depending upon which cube corner element is being considered.
- 10

- “Direct machining” refers to forming in the plane of a substrate one or more groove side surfaces typically by drawing a cutting tool along an axis substantially parallel to the plane of the substrate.
- 15

“Face” means a substantially smooth surface.

“Geometric structure” means a protrusion or cavity having a plurality of faces.

“Groove” means a cavity elongated along a groove axis and bounded at least in part by two opposed groove side surfaces.

- 20 “Groove side surface” means a surface or series of surfaces capable of being formed by drawing one or more cutting tools across a substrate in a substantially continuous linear motion. Such motion includes fly-cutting techniques where the cutting tool has a rotary motion as it advances along a substantially linear path.

- “Nondihedral edge” of a cube corner element is an edge of one of the three faces of the cube corner element that is not a dihedral edge of such cube corner element. Note that any particular edge on a structured surface may or may not be a nondihedral edge, depending upon which cube corner element is being considered.
- 25

“PG cube corner element” stands for “preferred geometry” cube corner element, and is defined in the context of a structured surface of cube corner elements that extends along a reference plane. For the purposes of this application, a PG cube corner element means a cube corner element that has at least one nondihedral edge that: (1) is nonparallel to the reference plane; and (2) is substantially parallel to an adjacent nondihedral edge of a neighboring cube corner element. A cube corner element whose three reflective faces are all rectangles (inclusive of squares) is one example of a PG cube corner element.

“Protrusion” has its broad ordinary meaning, and can comprise a pyramid.

“Pyramid” means a protrusion having three or more side faces that meet at a vertex, and can include a frustum.

“Reference plane” means a plane or other surface that approximates a plane in the vicinity of a group of adjacent cube corner elements or other geometric structures, the cube corner elements or geometric structures being disposed along the plane.

“Retroreflective” means having the characteristic that obliquely incident incoming light is reflected in a direction antiparallel to the incident direction, or nearly so, such that an observer at or near the source of light can detect the reflected light.

“Structured” when used in connection with a surface means a surface that has a plurality of distinct faces arranged at various orientations.

“Symmetry axis” when used in connection with a cube corner element refers to the vector that originates at the cube corner apex and forms an equal acute angle with the three faces of the cube corner element. It is also sometimes referred to as the optical axis of the cube corner element.

“Transition line” means a line or other elongated feature that separates constituent faces of a compound face.

“Waste pieces” means portions of the compound substrate that are discarded using the present fabrication methods.

1999 2000 2001 2002 2003 2004 2005 2006 2007 2008 2009 2010 2011 2012 2013 2014 2015 2016 2017 2018 2019 2020 2021 2022 2023 2024 2025 2026 2027 2028 2029 2030 2031 2032 2033 2034 2035 2036 2037 2038 2039 2040 2041 2042 2043 2044 2045 2046 2047 2048 2049 2050 2051 2052 2053 2054 2055 2056 2057 2058 2059 2060 2061 2062 2063 2064 2065 2066 2067 2068 2069 2070 2071 2072 2073 2074 2075 2076 2077 2078 2079 2080 2081 2082 2083 2084 2085 2086 2087 2088 2089 2090 2091 2092 2093 2094 2095 2096 2097 2098 2099 2100 2101 2102 2103 2104 2105 2106 2107 2108 2109 2110 2111 2112 2113 2114 2115 2116 2117 2118 2119 2120 2121 2122 2123 2124 2125 2126 2127 2128 2129 2130 2131 2132 2133 2134 2135 2136 2137 2138 2139 2140 2141 2142 2143 2144 2145 2146 2147 2148 2149 2150 2151 2152 2153 2154 2155 2156 2157 2158 2159 2160 2161 2162 2163 2164 2165 2166 2167 2168 2169 2170 2171 2172 2173 2174 2175 2176 2177 2178 2179 2180 2181 2182 2183 2184 2185 2186 2187 2188 2189 2190 2191 2192 2193 2194 2195 2196 2197 2198 2199 2200 2201 2202 2203 2204 2205 2206 2207 2208 2209 2210 2211 2212 2213 2214 2215 2216 2217 2218 2219 2220 2221 2222 2223 2224 2225 2226 2227 2228 2229 2230 2231 2232 2233 2234 2235 2236 2237 2238 2239 2240 2241 2242 2243 2244 2245 2246 2247 2248 2249 2250 2251 2252 2253 2254 2255 2256 2257 2258 2259 2260 2261 2262 2263 2264 2265 2266 2267 2268 2269 2270 2271 2272 2273 2274 2275 2276 2277 2278 2279 2280 2281 2282 2283 2284 2285 2286 2287 2288 2289 2290 2291 2292 2293 2294 2295 2296 2297 2298 2299 2300 2301 2302 2303 2304 2305 2306 2307 2308 2309 2310 2311 2312 2313 2314 2315 2316 2317 2318 2319 2320 2321 2322 2323 2324 2325 2326 2327 2328 2329 2330 2331 2332 2333 2334 2335 2336 2337 2338 2339 2340 2341 2342 2343 2344 2345 2346 2347 2348 2349 2350 2351 2352 2353 2354 2355 2356 2357 2358 2359 2360 2361 2362 2363 2364 2365 2366 2367 2368 2369 2370 2371 2372 2373 2374 2375 2376 2377 2378 2379 2380 2381 2382 2383 2384 2385 2386 2387 2388 2389 2390 2391 2392 2393 2394 2395 2396 2397 2398 2399 2400 2401 2402 2403 2404 2405 2406 2407 2408 2409 2410 2411 2412 2413 2414 2415 2416 2417 2418 2419 2420 2421 2422 2423 2424 2425 2426 2427 2428 2429 2430 2431 2432 2433 2434 2435 2436 2437 2438 2439 2440 2441 2442 2443 2444 2445 2446 2447 2448 2449 2450 2451 2452 2453 2454 2455 2456 2457 2458 2459 2460 2461 2462 2463 2464 2465 2466 2467 2468 2469 2470 2471 2472 2473 2474 2475 2476 2477 2478 2479 2480 2481 2482 2483 2484 2485 2486 2487 2488 2489 2490 2491 2492 2493 2494 2495 2496 2497 2498 2499 2500 2501 2502 2503 2504 2505 2506 2507 2508 2509 2510 2511 2512 2513 2514 2515 2516 2517 2518 2519 2520 2521 2522 2523 2524 2525 2526 2527 2528 2529 2530 2531 2532 2533 2534 2535 2536 2537 2538 2539 2540 2541 2542 2543 2544 2545 2546 2547 2548 2549 2550 2551 2552 2553 2554 2555 2556 2557 2558 2559 2560 2561 2562 2563 2564 2565 2566 2567 2568 2569 2570 2571 2572 2573 2574 2575 2576 2577 2578 2579 2580 2581 2582 2583 2584 2585 2586 2587 2588 2589 2590 2591 2592 2593 2594 2595 2596 2597 2598 2599 2600 2601 2602 2603 2604 2605 2606 2607 2608 2609 2610 2611 2612 2613 2614 2615 2616 2617 2618 2619 2620 2621 2622 2623 2624 2625 2626 2627 2628 2629 2630 2631 2632 2633 2634 2635 2636 2637 2638 2639 2640 2641 2642 2643 2644 2645 2646 2647 2648 2649 2650 2651 2652 2653 2654 2655 2656 2657 2658 2659 2660 2661 2662 2663 2664 2665 2666 2667 2668 2669 2670 2671 2672 2673 2674 2675 2676 2677 2678 2679 2680 2681 2682 2683 2684 2685 2686 2687 2688 2689 2690 2691 2692 2693 2694 2695 2696 2697 2698 2699 2700 2701 2702 2703 2704 2705 2706 2707 2708 2709 2710 2711 2712 2713 2714 2715 2716 2717 2718 2719 2720 2721 2722 2723 2724 2725 2726 2727 2728 2729 2730 2731 2732 2733 2734 2735 2736 2737 2738 2739 2740 2741 2742 2743 2744 2745 2746 2747 2748 2749 2750 2751 2752 2753 2754 2755 2756 2757 2758 2759 2760 2761 2762 2763 2764 2765 2766 2767 2768 2769 2770 2771 2772 2773 2774 2775 2776 2777 2778 2779 2780 2781 2782 2783 2784 2785 2786 2787 2788 2789 2790 2791 2792 2793 2794 2795 2796 2797 2798 2799 2800 2801 2802 2803 2804 2805 2806 2807 2808 2809 2810 2811 2812 2813 2814 2815 2816 2